



TRUHLÁŘ a spol., s.r.o.

Výrobce hmoždinek a spojovacího materiálu

PROHLÁŠENÍ O VLASTNOSTECH

Prohlášení o vlastnostech číslo: 1343-CPR-M 636-3/03.19

Typ výrobku: Chemická malta – Vinylester

Harmonizovaná norma: EAD 330499-00-0601

Evropské technické schválení: ETA-08/0382 ze dne 16.5.2018

Identifikace výrobku: Chemická malta CM-V – Vinylester

Účel použití výrobku: Chemická injektovaná kotva do netrhlinového betonu
O velikosti M8, M10, M12, M16, M20

Výrobce: Truhlář a spol., s.r.o.
Klapkova 36
Praha 8, 18200

Výrobna: Truhlář a spol., s.r.o.
Plant 1, Německo

Systém posouzení shody: Systém 1 podle směrnice 305/2011/EU popsáný takto –
Certifikace shody výrobku notifikovanou osobou založeném na
těchto základech:
(a) Úkoly výrobce:
(1) Systém řízení výroby
(2) Zkoušení vzorků odebraných ve výrobě výrobcem musí být
podle kontrolního plánu
(b) Úkoly notifikované osoby
(3) Počáteční zkouška typu výrobku
(4) Počáteční inspekce v místě výroby a řízení výroby



TRUHLÁŘ a spol., s.r.o.

Výrobce hmoždinek a spojovacího materiálu

Tabulka č.1 Vlastnosti výrobku

Velikost	M8	M10	M12	M16	M20
osová vzdálenost	80 (min. 40)	90 (min. 50)	110 (min. 60)	130 (min. 70)	170 (min. 90)
vzdálenost od okraje	100 (min. 40)	120 (min. 50)	140 (min. 60)	170 (min. 70)	220 (min. 90)
min. vrtaná hloubka	80	90	110	125	170
průměr svorníku	8	10	12	16	20
průměr vrtání	10/14	12/16	14/18	18/24	22/30
kroucí moment - beton [Nm]	10	20	40	80	150
kroucí moment - porobeton [Nm]	5	8	8	-	-

Tabulka č.2 Nosnosti (kN)

Velikost	M8	M10	M12	M16	M20
Beton $\geq$ B25	5,6	8,8	12,3	17,5	24,5
Beton $\geq$ B15	4,3	6,8	9,5	13,5	19,0
Porovitý beton $\geq$ B15	1,2	1,2	1,2	-	-

Tabulka č.3 Doba tuhnutí a vytvrzení

Teplota*	Tuhnutí	Vytvrzení
- 5 °C	90 min.	360 min.
+/- 0 °C	45 min.	180 min.
+ 5 °C	25 min.	120 min.
+ 10 °C	15 min.	80 min.
+ 20 °C	6 min.	45 min.
+ 30 °C	4 min.	25 min.
+ 35 °C	2 min.	20 min.

* - teplota materiálu ve kterém je aplikována chemická malta

Toto prohlášení o vlastnostech se vydává na výhradní odpovědnost výrobce.

Vystaveno v Praze dne 26.9.2025



TRUHLÁŘ a spol., s.r.o.

Klapkova 36, 182 00 Praha 8
Sklad: Hlubočinka 812, 251 68 Praha-východ
Tel.: +420 323 671 745 Fax: +420 323 671 744

Radek Truhlář – jednatel společnosti

Certificate of constancy of performance

No. 1343-CPR-M 636-3/03.19

In compliance with Regulation 305/2011/EU of the European Parliament and of the Council of 9 March 2011 (the Construction products Regulation or CPR) this certificate applies to the construction product

TRUHLÁR Injection system
CM-V or CM-V Winter for concrete
Bonded fastener for use in concrete

TRUHLAR a spol., v.o.s.
Klapkova 36
182 00 PRAHA 8
TSSCHECHISCHE REPUBLIK

and produced in the manufacturing plant
TRUHLÁR a spol., v.o.s., Plant1 Germany.

This certificate attests that all provisions concerning the assessment and verification of constancy of performance described in the ETA

ETA-08/0382 of 16 May 2018


and

EAD 330499-00-0601

under system 1 for the performances set out in this certificate are applied and that the construction product fulfil all the prescribed requirements for these performances.

This certificate was first issued on 22/03/2019 and will remain valid as long as the ETA remains valid and the manufacturing conditions in the plant or the factory production control itself are not modified significantly, unless suspended or withdrawn by the product certification body.

Darmstadt, 22/03/2019



Dr.-Ing. P. Bender
Head of the notified certification body



Dipl.-Ing.(FH) F. Persichella
Technical responsible

